



NATO UNCLASSIFIED
Releasable to Interoperability Platform

21 March 2023

DOCUMENT
AC/112(NAVAL-FLWP)D(2023)0003

PETROLEUM COMMITTEE (PC)
NAVAL FUELS & LUBRICANTS WORKING PARTY (NAVAL FLWP)

**STUDY DRAFT 1 OF AFLP- 1385 (EDITION D)(VERSION 1) - GUIDE SPECIFICATION
(MINIMUM QUALITY STANDARDS) FOR NAVAL DISTILLATE FUELS (F-75 AND F-76)**

Note by the Staff Officer

Reference: AC/112(NAVAL-FLWP)DS(2022)0001, paragraph 4

1. Further to reference, the Netherlands Custodian prepared Study Draft 1 of AFLP-1385 (Edition D)(Version 1) at Enclosure 1. Additional changes were made to it with the deletion JFTOT requirements for Synthesized Paraffinic Diesel, requirements for lubricity (from max. 520 micrometer tot max. 460 micrometer), particulate contamination (from max. 15 mg/L to max. 10 mg/L) and filter blocking tendency test (from min. 150 ml to min. 250 ml).
2. Nations are invited to review the document and to send their comments to the Custodian (JRS.Aarden@mindef.nl), the Chair (gregory.s.toms.civ@us.navy.mil) and the Staff Officer (van-exem.philippe@hq.nato.int) by **Friday, 12 May 2023**.
3. The enclosed Study Draft 1 will be used as a basis for further discussion and decision at the 2023 NAVAL FLWP meeting in June.

(Signed) Philippe Van Exem

1 Enclosure

Action Officer: Mr. Van Exem, Ext.4564
Original: English



NATO UNCLASSIFIED
Releasable to IP

NATO STANDARD

AFLP-1385

GUIDE SPECIFICATION (MINIMUM QUALITY STANDARDS) FOR NAVAL DISTILLATE FUELS (F-75 AND F-76)

Edition D, Version 1
Study Draft 1



NORTH ATLANTIC TREATY ORGANIZATION

ALLIED FUELS AND LUBRICANTS PUBLICATION

Published by the
NATO STANDARDIZATION OFFICE (NSO)
© NATO/OTAN

NATO UNCLASSIFIED
Releasable to IP

NATO UNCLASSIFIED
Releasable to IP

INTENTIONALLY BLANK

NATO UNCLASSIFIED
Releasable to IP

NATO UNCLASSIFIED
Releasable to IP

NORTH ATLANTIC TREATY ORGANIZATION (NATO)

NATO STANDARDIZATION OFFICE (NSO)

NATO LETTER OF PROMULGATION

[DATE]

1. The enclosed Allied Fuels and Lubricants Publication AFLP-1385, Edition D, Version 1, GUIDE SPECIFICATION (MINIMUM QUALITY STANDARDS) FOR NAVAL DISTILLATE FUELS (F-75 AND F-76), which has been approved by the nations in the Petroleum Committee, is promulgated herewith. The agreement of nations to use this publication is recorded in STANAG 1385.
2. AFLP-1385, Edition D, Version 1, is effective upon receipt and supersedes AFLP-1385, Edition C, Version 1 which shall be destroyed in accordance with the local procedure for the destruction of documents.
3. This NATO standardization document is issued by NATO. In case of reproduction, NATO is to be acknowledged. NATO does not charge any fee for its standardization documents at any stage, which are not intended to be sold. They can be retrieved from the NATO Standardization Document Database (<https://nso.nato.int/nso/>) or through your national standardization authorities.
4. This publication shall be handled in accordance with C-M(2002)60.

Dimitrios SIGOULAKIS
Major General, GRC (A)
Director, NATO Standardization Office

NATO UNCLASSIFIED
Releasable to IP

NATO UNCLASSIFIED
Releasable to IP

INTENTIONALLY BLANK

NATO UNCLASSIFIED
Releasable to IP

RESERVED FOR NATIONAL LETTER OF PROMULGATION

INTENTIONALLY BLANK

INTENTIONALLY BLANK

INTENTIONALLY BLANK

TABLE OF CONTENTS

SECTION 1	GENERAL	1-1
SECTION 2	NATO GUIDE SPECIFICATION FOR NAVAL DISTILLATE FUEL NATO CODE F-75.....	2-1
SECTION 3	NATO GUIDE SPECIFICATION FOR NAVAL DISTILLATE FUEL NATO CODE F-76.....	3-1
SECTION 4A	REQUIREMENTS SYNTHESIZED PARAFFINIC DIESEL (SPD)	4-1
SECTION 4B	REQUIREMENTS SYNTHESIZED ISO-PARAFFINS	4-4

INTENTIONALLY BLANK

SECTION 1 GENERAL

0101. It is agreed that nations' specifications shall comply with these minimum requirements before the subjects of these specifications are accepted as standardized products under NATO Code Numbers F-75 or F-76.

0102. It is agreed that in order to promote product development, any nation's specifications may include additional tests or improved quality requirements to those in the guide specification.

0103. It is agreed that this guide specification shall be subject to review with the object of improving product quality as required by operational use.

0104. AFLP-1135 lists under NATO Code Numbers F-75 and F-76, national specifications which have been agreed as interchangeable.

0105. The quality standards contained in this document are to be used by Member Nations (MNs) in the preparation and maintenance of their individual procurement specifications and standards. A MNs' individual procurement document may be more stringent depending upon its equipment. This document is not designed to be used in the direct procurement of products.

0106. The finished fuel described in this document may contain synthesized components, which shall conform to the requirements in either Section 4A or 4B.

0107. Finished fuel containing synthesized components shall conform to the properties listed in Section 2 and Section 3.

0108. Before any fuel containing synthetic components may be delivered to a nation, it must first be ascertained that the appropriate clearance document(s), permitting its use, have been obtained. Typically, clearances would be provided by the national technical authority for the fuel, in communication with e.g. the Original Equipment Manufacturer (OEM) and/or ship engineering officer.

INTENTIONALLY BLANK

SECTION 2 NATO GUIDE SPECIFICATION FOR NAVAL DISTILLATE FUEL NATOCODE F-75

COMPOSITION F-75: Exclusive base materials		Distillate from crude oil or from blends of hydrocarbon distillates derived from crude oil and approved ⁽²⁾ synthetic fuel.		
Content of synthetic components		Max. 50% v/v Synthesized Paraffinic Diesel ⁽³⁾ (SPD) derived from Fischer-Tropsch (FT) ⁽⁴⁾ or Hydro processed Renewable Diesel (HRD) ⁽⁵⁾ methods AND remainder: distillate derived from crude oil. or: Max. 20% v/v Synthesized Iso-Paraffins ⁽⁶⁾ derived from hydroprocessed fermented sugars AND remainder: distillate derived from crude oil.		
Additives		Approved additives, type and concentration shall be declared.		
SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
1.	Appearance		Visual Examination or ASTM D4176	Clear and bright, free from impurities and separated water at temperatures between 10 and 25 °C
2.	Density at 15 °C	kg/m ³	ISO 3675	815.0-880.0
3.	Colour	-	ISO 2049	Max. 3.5
4.	Ash content	% m/m	ISO 6245	Max. 0.010
5.	Carbon residue:			
5.1	Carbon residue, Ramsbottom (on 10% distillation residues) or 5.2	% m/m	ISO 4262	Max. 0.2
5.2	Carbon residue, Conradson	% m/m	ISO 10370	Max. 0.16
6.	Copper corrosion (3hr at 100°C)	class	ISO 2160	Max. 1
7.	Cloud point	° C	ISO 3015	Max. -12
8.	Pour point	° C	ISO 3016	Max. -18
9.	Flash point, closed cup	° C	ISO 2719	Min. 60
10.	Ignition quality ⁽⁷⁾ :			
10.1	Cetane number or 10.2 ⁽⁸⁾	-	ISO 5165	Min. 43
10.2	Cetane index	-	ASTM D976	Min. 46
11.	Sulphur content	% m/m	ISO 14596 or ASTM D4294 or ASTM D5453 ⁽⁹⁾	Max. 0.10
12.	Distillation:		ISO 3405	
12.1	10% recovered	°C		Report
12.2	50% recovered	°C		Report
12.3	90% recovered	°C		Max. 357
12.4	Final Boiling Point	°C		Max. 385
12.5	Residue plus loss at FBP	% v/v		Max. 3
13.	Viscosity, kinematic (40 ° C)	mm ² /s	ISO 3104	1.700 – 4.300
14.	Neutralisation:			
14.1	Acid number	mg KOH/g	ISO 6618	Max. 0.5
14.2	Inorganic acidity	mg KOH/g	IP 182	Nil

SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
15.	Water and sediment by centrifuge ⁽¹⁰⁾	% v/v	ISO 3734	Max. 0.05
16.	Storage stability:			
16.1	Oxidation stability of middle-distillate fuels or 16.2	g/m ³	ISO 12205	Max. 15
16.2	Distillate Fuel Storage Stability at 43°C (110°F)	mg/100 ml	IP 378/ASTM D4625	Max. 1.0
17.	Water separation:			
17.1	Demulsibility or 17.2	minutes	ISO 6614	Max. 10
17.2	Water reaction	ml	Def.Stan. 91-4 Annex A	Max. 2.0
18.	Lubricity: Wear scar diameter ⁽¹¹⁾	µm	ISO 12156-1	Max 460
19.1	Particulate contamination or 19.2	mg/l	ASTM D6217 or ASTM D5452	Max. 10
19.2	Filter Blocking Tendency Test ⁽¹²⁾	ml	IP 387 procedure A ASTM D2068	Min. 250
20.	Aromatics ⁽¹³⁾	%m/m	D6591, D2425	Min. 8.1
21.	FAME ⁽¹⁴⁾ content	% v/v	EN 14078 or ASTM D7963	Max. 0.10

NOTES:

1. Where possible, an international standard test method is listed for the specified fuel properties. A national standard test method may also be listed, but in all cases, each nation is free to use their own equivalent national test method.
2. Approved synthetic fuels derived from:
 - Hydro processing of animal fat, plant oil or algal oil triglycerides (esters and fatty acids) or
 - Synthesis gas using the Fisher-Tropsch (FT) process or
 - Synthesized iso-paraffins made from fermentable sugars within approved concentration limits as set in national specifications.
3. Synthetic diesel fuel, derived from biomass, coal or natural gas, which has similar characteristics to mineral based diesel fuel.
4. A catalysed chemical reaction in which synthesis gas, a mixture of carbon monoxide and hydrogen, is converted into liquid hydrocarbons of various forms.
5. Fuel produced from mono-, di- and triglycerides, free fatty acids and fatty acid esters from plant, algae oils or animal fats that have been hydroprocessed to remove essentially all oxygen
6. Synthesized Iso-paraffins (farnesane) are produced by fermentation of sugars (farnesene), and sequentially hydro processing and fractionation to farnesane.
7. The Ignition Quality limits are based on F-75 fuel not containing cetane improvers.
8. If the F-75 contains synthetic components the calculation of Cetane Index is not reliable and therefore Cetane Number has to be declared instead of Cetane Index.
9. Test method ISO 14596 is recommended for the sulphur content range below 0.2 % m/m. ASTM D4294 is recommended for the sulphur content range 0.015 to 1.00 % m/m, ASTM D5453 is recommended for the sulphur content range 0.0001 to 0.015 % m/m.
10. This test should only apply if the fuel (sample) is not clear and bright
11. The Lubricity requirement only applies if the sulphur content is equal or less than 500 mg/kg (0.05% m/m).
12. The Particulate Contamination test and the Filter Blocking Tendency test are separate tests of which the results do not correlate. Each nation specifies the test to be used in the national specification(s). For the Filter Blocking Tendency test both procedures A and B are permitted.
13. The test should apply if the F-75 contains synthetic components (the minimum aromatic content is needed for fuel system seal swell).
14. Deliberate blending of FAME into F-75 is not allowed. However, some F-76 may contain FAME as a result of cross contamination in refinery processes or transport vectors with distillate stocks containing FAME

SECTION 3 NATO GUIDE SPECIFICATION FOR NAVAL DISTILLATE FUEL NATO CODE F-76

COMPOSITION F-76: Exclusive base materials		Distillate from crude oil or from blends of hydrocarbon distillates derived from crude oil and approved ⁽²⁾ synthetic fuel.		
Content of synthetic components		Max. 50% v/v Synthesized Paraffinic Diesel ⁽³⁾ (SPD) derived from Fischer-Tropsch (FT) ⁽⁴⁾ or Hydro processed Renewable Diesel (HRD) ⁽⁵⁾ methods AND remainder: distillate derived from crude oil. or: Max. 20% v/v Synthesized Iso-Paraffins ⁽⁶⁾ derived from hydroprocessed fermented sugars AND remainder: distillate derived from crude oil.		
Additives		Approved additives, type and concentration shall be declared.		
SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
1.	Appearance		Visual Examination or ASTM D4176	Clear and bright, free from impurities and separated water at temperatures between 10 and 25 °C
2.	Density at 15 °C	kg/m ³	ISO 3675	800.0-880.0
3.	Colour	-	ISO 2049	Matox. 3.5
4.	Ash content	% m/m	ISO 6245	Max. 0.010
5.	Carbon residue:			
5.1	Carbon residue, Ramsbottom (on 10% distillation residues) or 5.2	% m/m	ISO 4262	Max. 0.2
5.2	Carbon residue, Conradson	% m/m	ISO 10370	Max. 0.16
6.	Copper corrosion (3hr at 100°C)	class	ISO 2160	Max. 1
7.	Cloud point	° C	ISO 3015	Max. -1
8.	Pour point	° C	ISO 3016	Max. -6
9.	Flash point, closed cup	° C	ISO 2719	Min. 60
10.	Ignition quality ⁽⁷⁾ :			
10.1	Cetane number or 10.2 ⁽⁸⁾	-	ISO 5165	Min. 43
10.2	Cetane index	-	ASTM D976	Min. 46
11.	Sulphur content	% m/m	ISO 14596 or ASTM D4294 or ASTM D5453 ⁽⁹⁾	Max. 0.10
12.	Distillation:		ISO 3405	
12.1	10% recovered	°C		Report
12.2	50% recovered	°C		Report
12.3	90% recovered	°C		Max. 357
12.4	Final Boiling Point	°C		Max. 385
12.5	Residue plus loss at FBP	% v/v		Max. 3
13.	Viscosity, kinematic (40 ° C)	mm ² /s	ISO 3104	1.700 – 4.300
14.	Neutralisation:			
14.1	Acid number	mg KOH/g	ISO 6618	Max. 0.5
14.2	Inorganic acidity	mg KOH/g	IP 182	Nil
15.	Water and sediment by centrifuge ⁽¹⁰⁾	% v/v	ISO 3734	Max. 0.05

F-76

SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
16. 16.1	Storage stability: Oxidation stability of middle-distillate fuels or <u>16.2</u>	g/m ³	ISO 12205	Max. 15
16.2	Distillate Fuel Storage Stability at 43°C (110°F)	mg/100 ml	IP 378/ASTM D4625	Max. 1.0
17. 17.1	Water separation: Demulsibility or <u>17.2</u>	minutes	ISO 6614	Max. 10
17.2	Water reaction	ml	Def.Stan. 91-4 Annex A	Max. 2.0
18.	Lubricity: Wear scar diameter ⁽¹¹⁾	µm	ISO 12156-1	Max 460
19.1	Particulate contamination or <u>19.2</u>	mg/l	ASTM D6217 or ASTM D5452	Max. 10
19.2	Filter Blocking Tendency Test ⁽¹²⁾	ml	IP 387 procedure A ASTM D2068	Min. 250
20.	Aromatics ⁽¹³⁾	%m/m	D6591, D2425	Min. 8.1
21.	FAME ⁽¹⁴⁾ content	% v/v	EN 14078 or ASTM D7963	Max. 0.10

NOTES:

1. Where possible, an international standard test method is listed for the specified fuel properties. A national standard test method may also be listed, but in all cases, each nation is free to use their own equivalent national test method.
2. Approved synthetic fuels derived from:
 - Hydro processing of animal fat, plant oil or algal oil triglycerides (esters and fatty acids) or
 - Synthesis gas using the Fisher-Tropsch (FT) process or
 - Synthesized iso-paraffins made from fermentable sugars within approved concentration limits as set in national specifications.
3. Synthetic diesel fuel, derived from biomass, coal or natural gas, which has similar characteristics to mineral based diesel fuel.
4. A catalysed chemical reaction in which synthesis gas, a mixture of carbon monoxide and hydrogen, is converted into liquid hydrocarbons of various forms.
5. Fuel produced from mono-, di- and triglycerides, free fatty acids and fatty acid esters from plant, algae oils or animal fats that have been hydroprocessed to remove essentially all oxygen
6. Synthesized Iso-paraffins (farnesane) are produced by fermentation of sugars (farnesene), and sequentially hydro processing and fractionation to farnesane.
7. The Ignition Quality limits are based on F-76 fuel not containing cetane improvers.
8. If the F-76 contains synthetic components the calculation of Cetane Index is not reliable and therefore Cetane Number has to be declared instead of Cetane Index.
9. Test method ISO 14596 is recommended for the sulphur content range below 0.2 % m/m. ASTM D4294 is recommended for the sulphur content range 0.015 to 1.00 % m/m, ASTM D5453 is recommended for the sulphur content range 0.0001 to 0.015 % m/m.
10. This test should only apply if the fuel (sample) is not clear and bright
11. The Lubricity requirement only applies if the sulphur content is equal or less than 500 mg/kg (0.05% m/m).
12. The Particulate Contamination test and the Filter Blocking Tendency test are separate tests of which the results do not correlate. Each nation specifies the test to be used in the national specification(s). For the Filter Blocking Tendency test both procedures A and B are permitted.
13. The test should apply if the F-76 contains synthetic components (the minimum aromatic content is needed for fuel system seal swell).
14. Deliberate blending of FAME into F-76 is not allowed. However, some F-76 may contain FAME as a result of cross contamination in refinery processes or transport vectors with distillate stocks containing FAME

SECTION 4A REQUIREMENTS SYNTHESIZED PARAFFINIC DIESEL (SPD)

COMPOSITION SPD:	
Exclusive base materials	Approved ⁽²⁾ synthetic fuel derived from biomass, coal or natural gas.
Manufacture	Synthesized Paraffinic Diesel ⁽³⁾ (SPD) derived from Fischer-Tropsch (FT) ⁽⁴⁾ or Hydro processed Renewable Diesel (HRD) ⁽⁵⁾ methods.
Additives	Approved additives, type and concentration shall be declared.
Antioxidants	Concentration: 17.2-24.0 mg/L ⁽⁶⁾

SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
1.	Appearance		Visual Examination or ASTM D4176	Clear and bright, free from impurities and separated water at temperatures between 10 and 25 °C
2.	Density at 15 °C	kg/m ³	ISO 3675	770-805
3.	Carbon residue:			
3.1	Carbon residue, Ramsbottom (on 10% distillation residues)	% m/m	ISO 4262	Max. 0.20
	or <u>3.2</u>			
3.2	Carbon residue, Conradson	% m/m	ISO 6615	Max. 0.14
4.	Copper corrosion (3hr at 100°C)	class	ISO 2160	Max. 1
5.	Cloud point	°C	ISO 3015	Max. -1
6.	Flash point, closed cup	°C	ISO 2719	Min. 60.0
7.	Derived Cetane Number	-	ASTM D6890, ASTM D7170	42-80
8.	Sulphur content	mg/kg	ASTM D5453 ⁽⁷⁾ or ASTM D2622	Max. 15
9.	Distillation:		ISO 3405	
9.1	10% recovered	°C		191-290
9.2	50% recovered	°C		Report
9.3	90% recovered	°C		290-357
9.4	Final Boiling Point	°C		300-385
9.5	T90-T10	°C		Min. 20
9.6	Residue plus loss at FBP	% v/v		Max. 3.0
10.	Viscosity, kinematic (40 °C)	mm ² /s	ISO 3104	1.700 – 4.300
11.	Neutralisation:			
11.1	Acid number	mg KOH/g	ISO 6618	Max. 0.08
11.2	Inorganic acidity or <u>11.3</u>	mg KOH/g	IP 182	Nil
11.3	Neutrality	mg KOH/g	ASTM D1093	Neutral
12.	Water separation characteristics ⁽⁸⁾	-	ASTM D7261	Min. 85
13.	Particulate contamination	mg/l	ASTM D6217 or ASTM D5452	Max. 1.0
14.	Aromatics	%m/m	ISO 12916, ASTM D2425	Max. 0.5
15.	Heat of Combustion	MJ/kg	ASTM D4809	Min. 43.5
16.	Hydrogen Content	% m/m	ASTM D7171, ASTM D4808, ASTM D5291	Min. 14.5

SYNTHESIZED PARAFFINIC DIESEL

SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
17.	Total Water	mg/kg	ASTM D6304	Max. 100
18.	Metals (Al, Ca, Co, Cr, Cu, Fe, Mg, Mn, Mo, Ni, P, Pb, Pd, Pt, Sn, Sr, Ti, V, Zn)	mg/kg	ASTM D7111	Max. 0.1 for each element

NOTES:

1. Where possible, an international standard test method is listed for the specified fuel properties. A national standard test method may also be listed, but in all cases, each nation is free to use their own equivalent national test method.
2. Approved synthetic fuels: derived from hydro processing of animal fat, plant oil or algal oil triglycerides (esters and fatty acids) or from synthesis gas using the Fisher-Tropsch (FT) process within approved concentration limits as set in national specifications. Any synthetic blend components must be tested to and certified to existing national standards.
3. Synthetic diesel fuel, derived from biomass, coal or natural gas, which has similar characteristics to mineral based diesel fuel.
4. A catalysed chemical reaction in which synthesis gas, a mixture of carbon monoxide and hydrogen, is converted into liquid hydrocarbons of various forms.
5. Fuel produced from mono-, di- and triglycerides, free fatty acids and fatty acid esters from plant, algae oils or animal fats that have been hydroprocessed to remove essentially all oxygen.
6. Antioxidant shall be added as soon as practicable after hydroprocessing or fractionation synthesizing and prior to the product or component being passed into storage to prevent peroxidation and gum formation after manufacture. Not less than 17.2 mg/L or more than 24.0 mg/L of active ingredient shall be used. The following antioxidant formulations are approved:
 - a. 2,6-di-tert-butyl-4-methylphenol.
 - b. 6-tert-butyl-2,4-dimethylphenol.
 - c. 2,6-di-tert-butylphenol.
 - d. 75 percent minimum 2,6-di-tert-butylphenol and;
25 percent maximum tert-butylphenols and tri-tert-butylphenols.
 - e. 72 percent minimum 6-tert-butyl-2,4-dimethylphenol and;
28 percent maximum tert-butyl-methylphenols and tert-butyl-dimethylphenols.
 - f. 55 percent minimum 2,4-dimethyl-6-tert-butylphenol and;
15 percent minimum 2,6-di-tert-butyl-4-methylphenol and;
30 percent maximum mixed methyl and dimethyl tert-butylphenols
7. ASTM D5453 is recommended for the sulphur content range 0.0001 to 0.015 % m/m. ASTM D2622 is recommended for the sulphur content range 3 mg/kg to 4,6 % m/m.
8. At point of Manufacture.

SECTION 4B REQUIREMENTS SYNTHESIZED ISO-PARAFFINS

COMPOSITION SIP:	
Exclusive base materials	Farnesene produced from fermentable sugars ⁽²⁾ .
Manufacture	Synthesized iso-paraffins are produced by fermentation, hydro processing and fractionation of the base materials ⁽³⁾ .
Additives	Approved additives, type and concentration shall be declared.
Antioxidants	Concentration: 17.2-24.0 mg/L ⁽⁴⁾

SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
1.	Appearance		Visual Examination or ASTM D4176	Clear and bright, free from impurities and separated water at temperatures between 10 and 25 °C
2.	Density at 15 °C	kg/m ³	ISO 3675	765-780
3.	Cloud point	°C	ISO 3015	Max. -70
4.	Flash point, closed cup	°C	ISO 2719	Min. 100.0
5.	Derived Cetane Number	-	ASTM D6890, ASTM D7170	42-80
6.	Sulphur content	mg/kg	ASTM D5453 ⁽⁵⁾ or ASTM D2622	Max. 2
7.	Distillation:		ISO 3405	
7.1	10% recovered	°C		250
7.2	50% recovered	°C		Report
7.3	90% recovered	°C		Report
7.4	Final Boiling Point	°C		255
7.5	T90-T10	°C		Max. 5.0
	Residue plus loss at FBP	% v/v		Max. 3.0
8.	Neutralisation:			
8.1	Acid number	mg KOH/g	ISO 6618	Max. 0.015
8.2	Inorganic acidity or <u>8.3</u>	mg KOH/g	IP 182	Nil
8.3	Neutrality	mg KOH/g	ASTM D1093	Neutral
9.	Heat of Combustion	MJ/kg	ASTM D4809	Min. 43.5
10.	Water separation characteristics ⁽⁶⁾	-	ASTM D7261	Min. 85
11.	Particulate contamination	mg/l	ASTM D6217 or ASTM D5452	Max. 1.0
12.	Total Water	mg/kg	ASTM D6304	Max. 75
13.	Thermal Stability:			
13.1	Change in Pressure Drop	mm Hg	ASTM D3241 ⁽⁷⁾	Max. 25
13.2	Tube rating: One of the following requirements shall be met ⁽⁸⁾ :			
13.2.1	Visual Tube Rating or <u>13.2.2</u>		Annex A1 (ASTM D3241)	Max. 3 (No peacock or abnormal color deposits)
13.2.2	Interferometric Rating or Ellipsometric Rating	nm average over area of 2.5 mm ²	Annex A2/A3 (ASTM D3241)	Max. 85
14.	Aromatics	%m/m	ISO 12916, ASTM D2425	Max. 0.5

SYNTHESIZED ISO-PARAFFINS

SER	PROPERTY	UNIT	METHOD ⁽¹⁾	LIMIT
15.	Bromine number	mg Br2/100g	ASTM D2710	Max. 300
16.	Hexahydrofarnesol	%m/m	ASTM D7974	Max. 1.5
17.	Farnesane	%m/m	ASTM D7974	Min. 97
18.	Metals (Al, Ca, Co, Cr, Cu, Fe, Mg, Mn, Mo, Ni, P, Pb, Pd, Pt, Sn, Sr, Ti, V, Zn)	mg/kg	ASTM D7111	Max. 0.1 for each element

NOTES:

1. Where possible, an international standard test method is listed for the specified fuel properties. A national standard test method may also be listed, but in all cases, each nation is free to use their own equivalent national test method.
2. Synthetic iso-paraffins (farnasene) are manufactured from fermented sugars derived from lignocellulosic biomass or sugarcane.
3. Farnesene is produced through fermentation of sugars by a special yeast. Target genes are selected to change the yeast's metabolism, converting the yeast from an ethanol-producing organism into a hydrocarbon producing organism. The unsaturated Farnesene will be hydroprocessed which will result in the saturated Farnesane.
4. Antioxidant shall be added as soon as practicable after hydroprocessing or fractionation synthesizing and prior to the product or component being passed into storage to prevent peroxidation and gum formation after manufacture. Not less than 17.2 mg/L or more than 24.0 mg/L of active ingredient shall be used. The following antioxidant formulations are approved:
 - a. 2,6-di-tert-butyl-4-methylphenol.
 - b. 6-tert-butyl-2,4-dimethylphenol.
 - c. 2,6-di-tert-butylphenol.
 - d. 75 percent minimum 2,6-di-tert-butylphenol and;
25 percent maximum tert-butylphenols and tri-tert-butylphenols.
 - e. 72 percent minimum 6-tert-butyl-2,4-dimethylphenol and;
28 percent maximum tert-butyl-methylphenols and tert-butyl-dimethylphenols.
 - f. 55 percent minimum 2,4-dimethyl-6-tert-butylphenol and;
15 percent minimum 2,6-di-tert-butyl-4-methylphenol and;
30 percent maximum mixed methyl and dimethyl tert-butylphenols
5. ASTM D5453 is recommended for the sulphur content range 0.0001 to 0.015 % m/m. ASTM D2622 is recommended for the sulphur content range 3 mg/kg to 4,6 % m/m.
6. At point of Manufacture.
7. Test performed at 325°C.
8. Tube deposit ratings shall be measured by Interferometric Rating or Ellipsometric Rating, when available. If the Interferometric Rating reports "N/A" for a tube's volumemeasurement, the test shall be a failure and the value reported as >85 nm. Visual rating of the heater tube by the method in D3241 Annex A1 is not required when Annex A2 or Annex A3 deposit thickness measurements are reported. In case of dispute between results from visual and metrological methods, the referee shall be considered the Annex A3 method if available, otherwise Annex A2

INTENTIONALLY BLANK

NATO UNCLASSIFIED
Releasable to IP

AFLP-1385(D)(1)

NATO UNCLASSIFIED
Releasable to IP